



FEBRUARY 2017

Ezda 3

Product

Pressure Die-casting Alloy.

Applications

Widely used alloy in the Die Casting Industry when zinc castings are required

Specification

Ezda 3

Aluminium: 3.9 – 4.2%

Zinc: Balance

Available in 9.4Kg ingots

Melting range 384 -387°C

THIS DATA SHEET IS OFFERED SOLELY FOR YOUR INFORMATION, CONSIDERATION AND INVESTIGATION. CAGROUP PROVIDES NO WARRANTIES, EITHER EXPRESSED OR IMPLIED AND ASSUMES NO RESPONSIBILITY FOR THE ACCURACY OR COMPLETENESS OF THE DATA CONTAINED HEREIN. MATERIAL USE BEYOND THE CONTROL OF SUPPLIER

MELBOURNE (Head Office):

32 Industrial Avenue.
Thomastown, Vic. 3074
Telephone: (03) 8301 7100
Facsimile: (03) 9359 4076

SYDNEY:

5 Coates Place,
Wetherill Park, N.S.W. 2164
Telephone: (02) 8795 6300
Facsimile: (02) 9756 4074

BRISBANE:

62 Parramatta Road,
Underwood, Qld. 4119
Telephone: (07) 3086 7300
Facsimile: (07) 3209 3611

PERTH:

Unit 10, 305 Victoria Road
Malaga, W.A. 6090
Telephone: (08) 9207 9300
Facsimile: (08) 9248 9543